

# APPLICATION UNDER UNITED STATES PATENT LAWS

Atty. Dkt. No. PW 279213  
(M#)

Invention: PERPENDICULAR MAGNETIC RECORDING MEDIUM

Inventor (s): OIKAWA et al.

Pillsbury Winthrop LLP  
Intellectual Property Group  
1100 New York Avenue, NW  
Ninth Floor  
Washington, DC 20005-3918  
Attorneys  
Telephone: (202) 861-3000

This is a:

- ☐ Provisional Application
- ☒ Regular Utility Application
- ☐ Continuing Application
  - ☒ The contents of the parent are incorporated by reference
- ☐ PCT National Phase Application
- ☐ Design Application
- ☐ Reissue Application
- ☐ Plant Application
- ☐ Substitute Specification
  - Sub. Spec Filed \_\_\_\_\_
  - in App. No. \_\_\_\_\_ / \_\_\_\_\_
- ☐ Marked up Specification re  
Sub. Spec. filed \_\_\_\_\_  
In App. No \_\_\_\_\_ / \_\_\_\_\_

## SPECIFICATION

TITLE OF THE INVENTION

PERPENDICULAR MAGNETIC RECORDING MEDIUM

CROSS-REFERENCE TO RELATED APPLICATIONS

5 This application is based upon and claims the benefit of priority from the prior Japanese Patent Application No. 2000-287720, filed September 21, 2000, the entire contents of which are incorporated herein by reference.

BACKGROUND OF THE INVENTION

10 The present invention relates to a perpendicular magnetic recording medium, particularly, to a perpendicular magnetic recording medium comprising a ferromagnetic magnetic recording layer containing cobalt.

15 In a perpendicular magnetic recording system, information is recorded by magnetization in the direction perpendicular to the recording medium surface. Compared with the areal magnetic recording system, the perpendicular magnetic recording system is  
20 low in demagnetizing field within each bit in performing a high density recording and, thus, is adapted for the improvement in the areal recording density.

25 Also, the perpendicular magnetic recording medium, in which a soft magnetic layer is arranged between the substrate and the perpendicular magnetic recording layer, performs the function of a so-called

"perpendicular double layered medium". The soft magnetic layer acts as the flux path to assist the recording magnetic field in refluxing between the magnetic head and the recording medium so as to improve the recording-reproducing efficiency. A cobalt-based material such as a CoCr alloy, a CoPt alloy or CoCrPt alloy is used in the perpendicular magnetic recording layer. Cobalt has a hexagonal close-packed structure (hcp structure). When a thin film of Co is formed, the easy magnetization axis of cobalt tends to be oriented in a direction perpendicular to the film surface. Therefore, Co is adapted for use in the preparation of a perpendicular magnetic recording layer.

In order to improve the magnetic recording characteristics, it is necessary to improve the perpendicular magnetic anisotropy of the Co-based recording layer and to promote the fineness of the crystal grains in the Co-based recording layer, thereby improving the coercive force and magnetostatic characteristics such as a perpendicular squareness ratio. To this end, known is a method that a nonmagnetic under layer such as a Ti layer is formed between a CoCr-based recording layer and a nonmagnetic substrate. This method is effective for improving the perpendicular orientation of the perpendicular magnetic recording layer. As described above, in the case of arranging a soft magnetic layer, the perpendicular

orientation of the Co-based magnetic recording layer is rendered poorer than in the case where the Co-based magnetic recording layer is formed in direct contact with the nonmagnetic substrate. It is possible to  
5 improve the perpendicular orientation of the magnetic recording layer by arranging an under layer such as a Ti layer between the soft magnetic layer and the magnetic recording layer in this case, too. However, for further improving the recording density, required  
10 is a nonmagnetic under layer that permit obtaining a higher orientation.

On the other hand, it was most popular in the past to use a material containing Co and Cr as main components for forming the perpendicular magnetic  
15 recording layer. It should be noted in this connection that Cr is segregated in the crystal grain boundary in the material containing Co and Cr as main components, making it possible to obtain a magnetic recording medium having a high coercive force and a high signal  
20 to noise ratio. However, it was impossible to obtain a sufficient perpendicular magnetic anisotropy by simply adding, for example, traces of Ta to the CoCr recording layer. On the other hand, a CoPt alloy recording layer exhibits a magnetic anisotropy larger than that  
25 exhibited by the elemental Co, though it is difficult to obtain a large coercive force and a high S/N ratio because Pt is not segregated in the grain boundary in

the case of the CoPt alloy recording layer. Such being the situation, it has been clarified that, in the recording layer prepared by adding Pt to the CoCr alloy, it is possible to obtain magnetic recording characteristics more excellent than those of the CoCr recording layer. A CoPtO recording layer prepared by adding oxygen to a CoPt magnetic layer is proposed in, for example, Japanese Patent Disclosure (Kokai) No. 7-235034, which corresponds to U.S. Patent No. 5,792,564, as a means for improving the magnetic recording characteristics of the magnetic recording layer. It is taught in the prior art that it is possible to prepare a magnetic recording medium exhibiting high perpendicular anisotropy and coercive force and satisfactory in the S/N ratio by forming a grain boundary layer rich in oxygen. A quite different method utilizing a multi-layered film consisting of a combination of Co and, for example, Pd has also been found. To be more specific, it has been found that a very high perpendicular anisotropy can be obtained by utilizing the interfacial magnetic anisotropy generated at the interface between Co and Pd. It has also been found that the S/N ratio can be improved to some extent by forming a segregation structure by, for example, an oxygen addition. However, since the matching of the lattice constant between Co and Pd or Pt is insufficient, the crystallinity of the multi-layered

film was not sufficiently high.

As described above, various combinations between the Co-based alloy and the materials of the under layer have been found in respect of the perpendicular magnetic recording medium using a Co-based alloy magnetic recording layer. However, further improvements are required for obtaining a perpendicular magnetic recording medium capable of exhibiting a satisfactory perpendicular anisotropy and a good S/N ratio and also capable of realizing a higher coercive force and a higher reproducing output.

The crystal orientation and the crystal grain diameter of the magnetic recording layer are greatly dependent on the surface state of the substrate. Therefore, even where a nonmagnetic under layer is applied, it is necessary to control the surface state of the substrate for further improving the perpendicular orientation the recording layer. Where, for example, Ti is used for forming the under layer, it is taught in, for example, Japanese Patent Disclosure No. 6-58734 that it is possible to obtain a surface state of the under layer, which can be perpendicularly oriented easily, by further forming a nonmagnetic layer made of Si, Ge or Sn between the substrate and the Ti under layer. It is described in the prior art quoted above that it is effective to form the nonmagnetic under layer of the double-layered structure between

a soft magnetic layer and a Co-based recording layer in a perpendicular double layered film. However, for further improving the recording density, it is required to develop a nonmagnetic under layer capable of obtaining a further improved orientation. Under the circumstances, various studies are being made in an attempt to arrive at new materials of the under layer and the combination of laminations of the under layers in each of the cases where a soft magnetic layer is arranged and not arranged between the under layer and the substrate. However, sufficient magnetic recording characteristics capable of fully coping with the demands for the further improvement of the recording density in the future have not yet been obtained when it comes to the nonmagnetic under layers published to date.

#### BRIEF SUMMARY OF THE INVENTION

An object of the present invention, which has been achieved in view of the situation described above, is to provide a magnetic recording medium capable of exhibiting a high coercive force and obtaining a high reproducing output by improving the perpendicular orientation of the Co-based magnetic recording layer.

According to a first aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a first under layer formed on the nonmagnetic substrate

and containing iron, a second under layer formed on the first under layer and containing mainly ruthenium, and a magnetic recording layer formed on the second under layer and containing mainly cobalt.

5           According to a second aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a first under layer formed on the nonmagnetic substrate and containing cobalt, a second under layer formed on  
10   the first under layer and containing mainly ruthenium, and a magnetic recording layer formed on the second under layer and containing mainly cobalt.

          According to a third aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate,  
15   a first under layer formed on the nonmagnetic substrate and containing mainly ruthenium, a second under layer formed on the first under layer and containing mainly cobalt, and a magnetic recording layer formed on the  
20   second under layer and containing mainly cobalt.

          According to a fourth aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a first under layer formed on the nonmagnetic substrate  
25   and containing titanium, a second under layer formed on the first under layer and containing mainly ruthenium, and a magnetic recording layer formed on the second



under layer and containing mainly cobalt.

According to a fifth aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a soft magnetic layer formed on the nonmagnetic substrate, a first under layer formed on the soft magnetic layer and containing as a main component at least one of vanadium and chromium, a second under layer formed on the first under layer and containing mainly ruthenium, and a magnetic recording layer formed on the second under layer and containing mainly cobalt.

According to a sixth aspect of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, and a magnetic recording layer formed on the nonmagnetic substrate and having a multi-layered structure prepared by alternately laminating a ferromagnetic layer containing mainly cobalt and a nonmagnetic layer containing mainly ruthenium.

According to the present invention, a perpendicular magnetic recording medium having a high coercive force and a high reproducing output can be obtained by disposing a nonmagnetic layer containing mainly ruthenium somewhere in the perpendicular magnetic recording medium. Such a non magnetic layer containing mainly ruthenium can be formed as a first under layer, and a layer containing another

suitable element is formed as a second under layer. Alternatively, a layer containing another suitable element is formed as a first under layer, and such a nonmagnetic layer containing mainly ruthenium  
5 is formed as a second under layer in the perpendicular magnetic recording medium of the present invention. Further, it is also possible to form a multi-layered magnetic recording layer by alternately laminating a Co-based magnetic layer and such Ru-based nonmagnetic  
10 layer so as to enable the perpendicular magnetic recording medium of the present invention to exhibit a high coercive force and a high reproducing output.

Additional objects and advantages of the invention will be set forth in the description which follows, and  
15 in part will be obvious from the description, or may be learned by practice of the invention. The objects and advantages of the invention may be realized and obtained by means of the instrumentalities and combinations particularly pointed out hereinafter.

20 BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING

The accompanying drawings, which are incorporated in and constitute a part of the specification, illustrate presently preferred embodiments of the invention, and together with the general description given above  
25 and the detailed description of the preferred embodiments given below, serve to explain the principles of the invention.

FIG. 1 schematically shows the construction of an example of a magnetic recording medium of the present invention;

FIG. 2 schematically shows the construction of another example of a magnetic recording medium of the present invention;

FIG. 3 schematically shows the construction of still another example of a magnetic recording medium of the present invention; and

FIG. 4 is a view showing the construction of an example of the magnetic recording apparatus in which the magnetic recording medium of the present invention can be applied.

#### DETAILED DESCRIPTION OF THE INVENTION

The perpendicular magnetic recording medium of the present invention comprises a nonmagnetic substrate and a Co-based perpendicular magnetic recording layer, and the present invention can be roughly classified into some types on the basis of the five view points described below.

In the perpendicular magnetic recording medium according to the first to fourth view points of the present invention, a first underlying and a second under layer are formed in the order mentioned between the nonmagnetic substrate and a Co-based perpendicular magnetic recording layer. Any one of the first, second under layers, contains ruthenium. The perpendicular

magnetic recording medium according to the first to fourth view points of the present invention is characterized as follows by the laminate structure consisting of a nonmagnetic layer containing ruthenium, a layer containing another element, and a Co-based perpendicular magnetic recording layer.

The first type of the present invention provides a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a first under layer formed on the nonmagnetic substrate and containing iron, a second under layer formed on the first under layer and containing mainly ruthenium, and a magnetic recording layer formed on the second under layer and containing mainly cobalt.

According to a preferred embodiment of the first type of the present invention, the first under layer consists essentially of iron. Alternatively, the first under layer contains iron as a main component and at least one element selected from the group consisting of aluminum, silicon, tantalum, carbon, zirconium, nitrogen and cobalt as an auxiliary component.

According to the first type of the present invention, it is possible to improve the perpendicular orienting properties and magnetic characteristics of a perpendicular magnetic recording medium having a Co-based, such as a CoPtO-based alloy by using an under layer of a laminate structure comprising a first

under layer consisting essentially of iron or  
containing iron as a main component and, preferably,  
a body-centered cubic crystal material described above,  
as an auxiliary component, and a second under layer  
5 containing ruthenium of a hexagonal close-packed  
structure. This construction is effective for ensuring  
a fineness and an uniformity of a crystal diameter in  
addition to an improvement of a crystal orientation in  
regard to the second under layer, therefore a fineness  
10 and an uniformity of a crystal diameter is promoted in  
addition to an improvement of a perpendicular crystal  
orientation in regard to the Co-based magnetic  
recording layer so as to decrease a transition noise  
and improve a recording resolution of the recording  
15 medium.

Preferred combinations of the main component and  
the auxiliary component include the combination of  
iron, tantalum and carbon, the combination of iron,  
zirconium and nitrogen, the combination of iron and  
20 cobalt, and the combination iron, aluminum and silicon.  
The iron alloy containing not higher than 10 atomic %  
of at least one of aluminum and silicon is called,  
for example, Sendust.

These preferred combinations are soft magnetic  
25 alloys having a high magnetic permeability.

Conventional Sendust, which is an iron alloy  
containing 5% of aluminum, 10% of silicon and the

remaining part 85% of iron, has a basic crystal structure equal to that of iron. A soft magnetic material having a high permeability can be obtained by adding Al and Si to an iron alloy. Even if the characteristics as a soft magnetic material are changed by the change of the addition amount within a range within which the basic crystal structure is not changed, the resultant medium can be expected to produce the similar effect.

In the second type of the present invention, the first under layer contains cobalt as a main component, and the second under layer contains ruthenium as a main component.

According to the second type of the present invention, the under layer is formed of a material of a hexagonal close-packed structure or an amorphous material containing cobalt as a main component. Also, the second under layer, which is laminated on the first under layer, is formed of ruthenium of a hexagonal close-packed structure. The particular construction of the under layers permits improving the perpendicular orienting properties and the magnetic properties of the perpendicular magnetic recording medium comprising a Co-based magnetic layer, particularly, a CoPtO-based magnetic layer. This construction is effective for ensuring a fineness and an uniformity of a crystal diameter in addition to an improvement of a crystal

orientation in regard to the second under layer,  
therefore a fineness and an uniformity of a crystal  
diameter is promoted in addition to an improvement of  
a perpendicular crystal orientation in regard to  
5 the Co-based magnetic recording layer so as to decrease  
a transition noise and improve a recording resolution  
of the recording medium.

In the preferred embodiment of the second type of  
the present invention, it is desirable for the first  
10 under layer to contain at least one auxiliary component  
selected from the group consisting of zirconium,  
niobium and chromium. Also, the preferred combinations  
of the main component and the auxiliary component  
includes a combination of cobalt, zirconium and niobium  
15 and a combination of cobalt and chromium. It is  
desirable for the alloy containing cobalt and chromium  
not to exhibit ferromagnetism. Also, the combination  
of cobalt, zirconium and niobium forms a soft magnetic  
alloy having a high magnetic permeability.

20 It is possible to use a soft magnetic alloy having  
a high permeability such as a CoZr-based alloy like  
CoZrNb, an FeCo-based alloy, an FeSi-based alloy,  
an FeTaC, FeZrN and NiFe-based alloy like Permalloy  
for forming a soft magnetic layer that is interposed  
25 between the nonmagnetic substrate and the perpendicular  
magnetic recording layer like the first under layer  
used in each of the first and second types of

the present invention.

The perpendicular magnetic recording medium using the particular soft magnetic material having a high magnetic permeability, which performs the function of a so-called "double layered perpendicular medium", performs a part of the function of the magnetic head that the recording magnetic field from the magnetic head is refluxed and is expected to produce excellent recording/reading characteristics interaction. Even in the case of using such a soft magnetic layer, the perpendicular orienting effect is considered to be substantially the same by applying an under layer of a laminate structure to the perpendicular magnetic recording layer.

In the third type of the present invention, the first under layer contains ruthenium as a main component, and the second under layer contains cobalt as a main component.

In the third type of the present invention, it is desirable for the second under layer to contain chromium as an auxiliary component. In this case, it is desirable for the cobalt-chromium alloy not to exhibit ferromagnetism.

Also, it is desirable for the first under layer to consist essentially of ruthenium.

According to the third type of the present invention, the first under layer is formed of



a material containing ruthenium of a hexagonal close-packed structure as a main component. Also, the second under layer, which is laminated on the first under layer, is formed of a material of a hexagonal close-packed structure containing cobalt as a main component. The particular construction makes it possible to improve the perpendicular orienting properties and the magnetic properties of the perpendicular magnetic recording medium comprising a Co-based magnetic layer, particularly, a CoPtO-based magnetic layer. This construction is effective for ensuring a fineness and an uniformity of a crystal diameter in addition to an improvement of a crystal orientation in regard to the second under layer, therefore a fineness and an uniformity of a crystal diameter is promoted in addition to an improvement of a perpendicular crystal orientation in regard to the Co-based magnetic recording layer so as to decrease a transition noise and improve a recording resolution of the recording medium.

According to the fourth type of the present invention, employed is a laminate structure formed on the substrate and comprising a first under layer containing titanium as a main component, a second under layer containing ruthenium as a main component and a perpendicular magnetic recording layer containing cobalt.

The nonmagnetic layer containing titanium, which is a material of a hexagonal close-packed structure and used as a first under layer, is formed of, for example, titanium or a compound selected from the group consisting of a nitride, a carbide and an oxide of titanium. It is also possible to use a titanium chromium alloy.

It is possible to form, for example, TiN having a NaCl structure by the sputtering of a TiN target under an argon gas atmosphere. Titanium and nitrogen are not necessarily bonded to each other at a ratio of 1:1 on the substrate, and it is considered that a nitride having a partially different ratio is formed. Further, substantially the same effect can be obtained in the case of forming an under layer formed of titanium alone. The similar effect on an improvement of a perpendicular orientation can be obtained in the cases where the under layer is formed of not only TiN but also a nitride having a different ratio and where a nitride and titanium are present together in the under layer. Further, the similar effect can be expected in respect of the carbide and oxide of titanium.

The chromium addition amount in TiCr suitable for the first under layer is not higher than 10 atomic %. Since titanium and chromium do not form a solid solution under room temperature, the basic crystal structure is similar to that of Ti and, thus, the

similar effect can be obtained sufficiently.

A layer containing ruthenium is used as the second under layer.

According to the present invention, a first under  
5 layer consisting of a specified nonmagnetic or soft  
magnetic material, a second under layer consisting of a  
specified nonmagnetic material, and a layer consisting  
of a ferromagnetic Co-based alloy material are formed  
on the substrate, thereby making the Co-based alloy  
10 layer, particularly, a CoPtO ferromagnetic layer having  
an excellent perpendicular orientation. As a result,  
it is possible to obtain a magnetic recording medium  
exhibiting a high coercive force and a high reproducing  
output.

15 Also, according to the present invention, it is  
possible to arrange a soft magnetic layer between the  
perpendicular magnetic recording medium relating to the  
first to fourth view points and the first under layer.

It should be noted in respect of the effects  
20 produced by the soft magnetic layer that the presence  
of the soft magnetic layer permits the resultant  
magnetic recording medium to perform the function of  
a perpendicular double layered medium and that the  
magnetic recording layer is enabled to produce  
25 excellent recording-reproducing characteristics by the  
interactive between the head and the soft magnetic  
layer.

Examples of the materials forming the soft magnetic layer include Sendust, Permalloy, ferrite, FeGaGe, FeGeSi, FeAlGa, FeRuGaSi, FeSi, FeCoNi, FeSiB, FeNiPb, FeSiC, FeCuNbSiB, FeZrB, FeZrBCu, CoFeSiB, 5 CoZrTa, and CoTi.

According to the fourth type of the present invention, the presence of the soft magnetic layer with the Co-based alloy magnetic recording layer permits the resultant magnetic recording medium to produce the 10 effect of a double layered medium, and it is possible to obtain the Co-based alloy magnetic recording layer, particularly, a CoPtO alloy layer, exhibiting excellent perpendicular orientation. As a result, it is possible to obtain a magnetic recording medium exhibiting a high 15 coercive force and a high reproducing output.

According to the fifth type of the present invention, there is provided a perpendicular magnetic recording medium, comprising a nonmagnetic substrate, a soft magnetic layer formed on the nonmagnetic 20 substrate, a first under layer formed on the soft magnetic layer, a second under layer formed on the first under layer and containing ruthenium, and a magnetic recording layer formed on the second under layer and containing mainly cobalt, wherein the first 25 under layer contains mainly at least one of the vanadium and chromium and is capable of optionally containing iron.

The produced effect and the preferred examples of the soft magnetic layer used are similar to those described previously.

According to the fifth type of the present invention, the presence of the soft magnetic layer with the Co-based alloy magnetic recording layer permits the resultant magnetic recording medium to produce the effect of a double layered medium, and it is possible to obtain the Co-based alloy magnetic recording layer, particularly, a CoPtO alloy layer, exhibiting excellent perpendicular orientation. As a result, it is possible to obtain a magnetic recording medium exhibiting a high coercive force and a high reproducing output.

It is desirable to use vanadium or chromium for forming the first under layer.

In the perpendicular magnetic recording medium according to the first to fifth types of the present invention, the material of the magnetic recording layer is not limited to the CoPtO alloy system. It is also possible for the magnetic recording layer to be formed of a CoCrPt-based alloy, or a multi-layered film system consisting of a Co film and a Pt film, consisting of a Co film and a Pd film or consisting of a Co film and a Ru film. The similar effect can be obtained even in the case where the film also contains oxygen. Also, the film containing ruthenium, which is used in the perpendicular magnetic recording medium according to

the first to fifth types of the present invention, consists essentially of ruthenium. However, it is possible to add another element such as Cr or Co to the film containing ruthenium.

5           According to the first to fifth types of the present invention, an appropriate combination of a layer containing ruthenium and another layer containing another element is used as the first and second under layers, and the particular combination is laminated  
10 below the perpendicular magnetic recording layer. As a result, the crystal orientation of the second under layer is improved by the first under layer. In addition, the crystal grains are made finer and uniform in the second under layer. Also, since the  
15 perpendicular magnetic recording layer is formed on the second under layer, the perpendicular orientation of the recording layer is improved by the presence of the second under layer. In addition, the crystal grains are microcrystallized and made uniform in the  
20 perpendicular magnetic recording layer. It follows that it is possible to suppress the transition noise of the recording medium and to improve the recording resolution of the recording medium.

25           Further, in order to prevent the under layer formed on the soft magnetic layer from being affected by the crystal orientation and the crystal grain diameter in the soft magnetic layer, it is possible to

form an amorphous material layer made of, for example, carbon on the soft magnetic layer.

It is also possible to form an antiferromagnetic layer such as an FeMn layer or an antimagnetic layer  
5 such as a CoSm layer between the non magnetic substrate and the soft magnetic layer to form an axis of a soft magnetic layer be uniform in the direction of circumference or radius.

According to the sixth type of the present  
10 invention, used is a multi-layered perpendicular magnetic recording layer having a multi-layered structure consisting of a Co-based magnetic layer and a Ru-based nonmagnetic layer that are alternately laminated one upon the other. The recording layer  
15 having the particular multi-layered structure permits further improving the perpendicular orientation and the perpendicular coercive force.

Also, according to the present invention, the multi-layered perpendicular magnetic recording layer  
20 can be used as the perpendicular magnetic recording layer according to the first to fifth view points of the present invention.

FIG. 1 shows an example of the construction of a magnetic recording medium 10 of the present  
25 invention. As shown in the drawing, the magnetic recording medium 10 comprises a substrate 1, a first under layer 2 formed on the substrate 1, a second under

layer 3 formed on the first under layer 2, a Co-based  
ferromagnetic layer 4 made of, for example, a CoPtO  
alloy and formed on the second under layer 3,  
and a protective layer 5 formed on the ferromagnetic  
5 layer 4.

Each of the layers laminate on the substrate 1 can  
be formed by a sputtering method with the materials of  
these layers used as targets.

FIG. 2 shows the construction of another example  
10 of a magnetic recording medium of the present  
invention. As shown in the drawing, the magnetic  
recording medium 20 shown in FIG. 2 is substantially  
equal in construction to the magnetic recording medium  
10 shown in FIG. 1, except that a laminate structure  
15 comprising a magnetic layer 4a, another magnetic layer  
4b and a nonmagnetic layer 6 made of ruthenium and  
interposed between the magnetic layers 4a and 4b is  
formed in place of the magnetic layer 4 shown in  
FIG. 1. Preferably, the nonmagnetic layer 6 should  
20 consist essentially of ruthenium. Where the magnetic  
layer is of a multi-layer structure constructed such  
that a nonmagnetic layer containing ruthenium as a main  
component, which is a nonmagnetic intermediate layer,  
is sandwiched between two adjacent ferromagnetic  
25 layers, it is possible to further improve the  
perpendicular orienting properties and the magnetic  
properties of the magnetic layer.



FIG. 3 is a cross sectional view showing still another example of the construction of a magnetic recording medium 30 of the present invention. As shown in the drawing, the magnetic recording medium 30 shown in FIG. 3 is substantially equal in construction to the magnetic recording medium 10 shown in FIG. 1, except that a soft magnetic layer 7 is interposed between the substrate 1 and the first under layer 2 in the magnetic recording medium 30 shown in FIG. 3.

The presence of the soft magnetic layer 7 permits the resultant magnetic recording medium 30 to perform the function of a double layered perpendicular film, and the magnetic recording medium 30 is expected to produce excellent recording/reading characteristics because of the interact between the head and the soft magnetic layer.

The present invention will now be described more in detail with reference the Examples which follow.

Example 1:

A glass substrate meeting the standard specification of a 2.5 inch magnetic disc was prepared as a nonmagnetic substrate. Each of the under layers, the magnetic layer, etc. was formed as described below on the glass substrate by means of DC magnetron sputtering.

In the first step, a iron layer was formed on the glass substrate as a first under layer in

a thickness of about 50 nm. Then, a ruthenium layer was formed as a second under layer on the iron layer in a thickness of about 37 nm.

5 In the next step, a CoPtCrO magnetic layer was formed on the second under layer by means of a sputtering of a CoPtCr alloy target under an argon atmosphere containing traces of O<sub>2</sub>. Incidentally, the CoPtCr alloy target contained 20 atomic % of Pt, 16 atomic % of Cr and the balance of Co. In this case, 10 used was a CoPtCr target having a relatively high Cr concentration. However, if the Cr concentration is not higher than 16 atomic %, an essential change in the construction of the magnetic layer is scarcely brought about by the Cr addition, making it possible to obtain 15 the similar effect as the characteristics of the medium.

20 Finally, a carbon layer having 10 nm of thickness was laminated as a protective layer on the magnetic layer so as to obtain a desired magnetic recording medium.

25 The magnetic characteristics of the resultant magnetic recording medium were measured by a vibrating sample type magnetometer (VSM), with the results as shown in Table 1. The mark "Hc $\perp$ " in Table 1 represents a coercive force in the case where a magnetic field is applied in a direction perpendicular to the film surface. Also, the mark "Hc//" in Table 1

represents a coercive force in the case where  
a magnetic field is applied to in a areal direction of  
the film surface. Further, the perpendicular  
squareness ratio represents a ratio of the residual  
5 magnetization to the saturated magnetization in the  
case of applying a magnetic field in a perpendicular  
direction.

Example 2:

A magnetic recording medium was prepared as in  
10 Example 1, except that a FeTaC layer having a thickness  
of about 100 nm was formed in place of the Fe layer.  
The FeTaC layer was formed by sputtering a FeTaC target  
containing 10 atomic % of Ta, 10 atomic % of C and  
the balance of Fe under an argon atmosphere. The  
15 magnetic properties of the magnetic recording medium  
thus obtained were measured as in Example 1, with  
the results as shown in Table 1.

Example 3:

A magnetic recording medium was prepared as in  
20 Example 1, except that a FeZrN layer having a thickness  
of about 100 nm was formed in place of the Fe layer.  
The FeZrN layer was formed by sputtering a FeZrN target  
containing 10 atomic % of Zr, 10 atomic % of N and the  
balance of Fe under an argon atmosphere. The magnetic  
25 properties of the magnetic recording medium thus  
obtained were measured as in Example 1, with the  
results as shown in Table 1.

Example 4:

A magnetic recording medium was prepared as in Example 1, except that a FeCo layer having a thickness of about 50 nm was formed in place of the Fe layer.

5 The FeCo layer was formed by sputtering a FeCo target containing 50 atomic % of Fe and the balance of Co under an argon atmosphere. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in  
10 Table 1.

Example 5:

A magnetic recording medium was prepared as in Example 1, except that a CoZrNb layer having a thickness of about 100 nm was formed in place of  
15 the Fe layer. The CoZrNb layer was formed by sputtering a CoZrNb target containing 5 atomic % of Zr, 10 atomic % of Nb and the balance of Co under an argon atmosphere. The magnetic properties of the magnetic recording medium thus obtained were measured as in  
20 Example 1, with the results as shown in Table 1.

Example 6:

A magnetic recording medium was prepared as in Example 1, except that a Co layer having a thickness of about 75 nm was formed in place of the Fe layer.

25 The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Example 7:

A magnetic recording medium was prepared as in Example 1, except that a CoCr layer having a thickness of about 40 nm was formed in place of the Fe layer.

5 The CoCr layer was formed by sputtering a CoCr target containing 33 atomic % of Cr and the balance of Co under an argon atmosphere. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in  
10 Table 1.

Example 8:

A magnetic recording medium was prepared as in Example 1, except that a ruthenium layer having a thickness of about 20 nm was formed as the first  
15 under layer in place of the Fe layer, and a CoCr layer having a thickness of about 15 nm was formed as the second under layer in place of the ruthenium layer. The CoCr layer was formed by sputtering a CoCr target containing 33 atomic % of Cr and the balance of Co  
20 under an argon atmosphere. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Comparative Example 1:

25 A magnetic recording medium was prepared as in Example 1, except that a Cr layer having a thickness of about 40 nm was formed in place of the Fe layer,

and the second under layer was not formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

5 Comparative Example 2:

A magnetic recording medium was prepared as in Example 1, except that the second under layer was not formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in  
10 Example 1, with the results as shown in Table 1.

Comparative Example 3:

A magnetic recording medium was prepared as in Example 2, except that the second under layer was not formed. The magnetic properties of the magnetic  
15 recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Comparative Example 4:

A magnetic recording medium was prepared as in Example 3, except that the second under layer was not  
20 formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Comparative Example 5:

A magnetic recording medium was prepared as in  
25 Example 4, except that the second under layer was not formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in

Example 1, with the results as shown in Table 1.

Comparative Example 6:

5 A magnetic recording medium was prepared as in Example 5, except that the second under layer was not formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Comparative Example 7:

10 A magnetic recording medium was prepared as in Example 6, except that the second under layer was not formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Comparative Example 8:

15 A magnetic recording medium was prepared as in Example 7, except that the second under layer was not formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

20 Comparative Example 9:

25 A magnetic recording medium was prepared as in Example 8, except that the second under layer was not formed. The magnetic properties of the magnetic recording medium thus obtained were measured as in Example 1, with the results as shown in Table 1.

Where the magnetic recording medium including a soft magnetic layer in addition to the recording

magnetic layer is measured by VSM, the resultant characteristics includes both of two characteristics relating to the soft magnetic layer and the magnetic recording layer. However since it is possible to  
5 interpret the characteristics separately in respect of Examples 1 to 6, the values for the recording layer approximately alone are shown.

11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65  
66  
67  
68  
69  
70  
71  
72  
73  
74  
75  
76  
77  
78  
79  
80  
81  
82  
83  
84  
85  
86  
87  
88  
89  
90  
91  
92  
93  
94  
95  
96  
97  
98  
99  
100  
101  
102  
103  
104  
105  
106  
107  
108  
109  
110  
111  
112  
113  
114  
115  
116  
117  
118  
119  
120  
121  
122  
123  
124  
125  
126  
127  
128  
129  
130  
131  
132  
133  
134  
135  
136  
137  
138  
139  
140  
141  
142  
143  
144  
145  
146  
147  
148  
149  
150  
151  
152  
153  
154  
155  
156  
157  
158  
159  
160  
161  
162  
163  
164  
165  
166  
167  
168  
169  
170  
171  
172  
173  
174  
175  
176  
177  
178  
179  
180  
181  
182  
183  
184  
185  
186  
187  
188  
189  
190  
191  
192  
193  
194  
195  
196  
197  
198  
199  
200  
201  
202  
203  
204  
205  
206  
207  
208  
209  
210  
211  
212  
213  
214  
215  
216  
217  
218  
219  
220  
221  
222  
223  
224  
225  
226  
227  
228  
229  
230  
231  
232  
233  
234  
235  
236  
237  
238  
239  
240  
241  
242  
243  
244  
245  
246  
247  
248  
249  
250  
251  
252  
253  
254  
255  
256  
257  
258  
259  
260  
261  
262  
263  
264  
265  
266  
267  
268  
269  
270  
271  
272  
273  
274  
275  
276  
277  
278  
279  
280  
281  
282  
283  
284  
285  
286  
287  
288  
289  
290  
291  
292  
293  
294  
295  
296  
297  
298  
299  
300  
301  
302  
303  
304  
305  
306  
307  
308  
309  
310  
311  
312  
313  
314  
315  
316  
317  
318  
319  
320  
321  
322  
323  
324  
325  
326  
327  
328  
329  
330  
331  
332  
333  
334  
335  
336  
337  
338  
339  
340  
341  
342  
343  
344  
345  
346  
347  
348  
349  
350  
351  
352  
353  
354  
355  
356  
357  
358  
359  
360  
361  
362  
363  
364  
365  
366  
367  
368  
369  
370  
371  
372  
373  
374  
375  
376  
377  
378  
379  
380  
381  
382  
383  
384  
385  
386  
387  
388  
389  
390  
391  
392  
393  
394  
395  
396  
397  
398  
399  
400  
401  
402  
403  
404  
405  
406  
407  
408  
409  
410  
411  
412  
413  
414  
415  
416  
417  
418  
419  
420  
421  
422  
423  
424  
425  
426  
427  
428  
429  
430  
431  
432  
433  
434  
435  
436  
437  
438  
439  
440  
441  
442  
443  
444  
445  
446  
447  
448  
449  
450  
451  
452  
453  
454  
455  
456  
457  
458  
459  
460  
461  
462  
463  
464  
465  
466  
467  
468  
469  
470  
471  
472  
473  
474  
475  
476  
477  
478  
479  
480  
481  
482  
483  
484  
485  
486  
487  
488  
489  
490  
491  
492  
493  
494  
495  
496  
497  
498  
499  
500  
501  
502  
503  
504  
505  
506  
507  
508  
509  
510  
511  
512  
513  
514  
515  
516  
517  
518  
519  
520  
521  
522  
523  
524  
525  
526  
527  
528  
529  
530  
531  
532  
533  
534  
535  
536  
537  
538  
539  
540  
541  
542  
543  
544  
545  
546  
547  
548  
549  
550  
551  
552  
553  
554  
555  
556  
557  
558  
559  
560  
561  
562  
563  
564  
565  
566  
567  
568  
569  
570  
571  
572  
573  
574  
575  
576  
577  
578  
579  
580  
581  
582  
583  
584  
585  
586  
587  
588  
589  
590  
591  
592  
593  
594  
595  
596  
597  
598  
599  
600  
601  
602  
603  
604  
605  
606  
607  
608  
609  
610  
611  
612  
613  
614  
615  
616  
617  
618  
619  
620  
621  
622  
623  
624  
625  
626  
627  
628  
629  
630  
631  
632  
633  
634  
635  
636  
637  
638  
639  
640  
641  
642  
643  
644  
645  
646  
647  
648  
649  
650  
651  
652  
653  
654  
655  
656  
657  
658  
659  
660  
661  
662  
663  
664  
665  
666  
667  
668  
669  
670  
671  
672  
673  
674  
675  
676  
677  
678  
679  
680  
681  
682  
683  
684  
685  
686  
687  
688  
689  
690  
691  
692  
693  
694  
695  
696  
697  
698  
699  
700  
701  
702  
703  
704  
705  
706  
707  
708  
709  
710  
711  
712  
713  
714  
715  
716  
717  
718  
719  
720  
721  
722  
723  
724  
725  
726  
727  
728  
729  
730  
731  
732  
733  
734  
735  
736  
737  
738  
739  
740  
741  
742  
743  
744  
745  
746  
747  
748  
749  
750  
751  
752  
753  
754  
755  
756  
757  
758  
759  
760  
761  
762  
763  
764  
765  
766  
767  
768  
769  
770  
771  
772  
773  
774  
775  
776  
777  
778  
779  
780  
781  
782  
783  
784  
785  
786  
787  
788  
789  
790  
791  
792  
793  
794  
795  
796  
797  
798  
799  
800  
801  
802  
803  
804  
805  
806  
807  
808  
809  
810  
811  
812  
813  
814  
815  
816  
817  
818  
819  
820  
821  
822  
823  
824  
825  
826  
827  
828  
829  
830  
831  
832  
833  
834  
835  
836  
837  
838  
839  
840  
841  
842  
843  
844  
845  
846  
847  
848  
849  
850  
851  
852  
853  
854  
855  
856  
857  
858  
859  
860  
861  
862  
863  
864  
865  
866  
867  
868  
869  
870  
871  
872  
873  
874  
875  
876  
877  
878  
879  
880  
881  
882  
883  
884  
885  
886  
887  
888  
889  
890  
891  
892  
893  
894  
895  
896  
897  
898  
899  
900  
901  
902  
903  
904  
905  
906  
907  
908  
909  
910  
911  
912  
913  
914  
915  
916  
917  
918  
919  
920  
921  
922  
923  
924  
925  
926  
927  
928  
929  
930  
931  
932  
933  
934  
935  
936  
937  
938  
939  
940  
941  
942  
943  
944  
945  
946  
947  
948  
949  
950  
951  
952  
953  
954  
955  
956  
957  
958  
959  
960  
961  
962  
963  
964  
965  
966  
967  
968  
969  
970  
971  
972  
973  
974  
975  
976  
977  
978  
979  
980  
981  
982  
983  
984  
985  
986  
987  
988  
989  
990  
991  
992  
993  
994  
995  
996  
997  
998  
999  
1000  
1001  
1002  
1003  
1004  
1005  
1006  
1007  
1008  
1009  
1010  
1011  
1012  
1013  
1014  
1015  
1016  
1017  
1018  
1019  
1020  
1021  
1022  
1023  
1024  
1025  
1026  
1027  
1028  
1029  
1030  
1031  
1032  
1033  
1034  
1035  
1036  
1037  
1038  
1039  
1040  
1041  
1042  
1043  
1044  
1045  
1046  
1047  
1048  
1049  
1050  
1051  
1052  
1053  
1054  
1055  
1056  
1057  
1058  
1059  
1060  
1061  
1062  
1063  
1064  
1065  
1066  
1067  
1068  
1069  
1070  
1071  
1072  
1073  
1074  
1075  
1076  
1077  
1078  
1079  
1080  
1081  
1082  
1083  
1084  
1085  
1086  
1087  
1088  
1089  
1090  
1091  
1092  
1093  
1094  
1095  
1096  
1097  
1098  
1099  
1100  
1101  
1102  
1103  
1104  
1105  
1106  
1107  
1108  
1109  
1110  
1111  
1112  
1113  
1114  
1115  
1116  
1117  
1118  
1119  
1120  
1121  
1122  
1123  
1124  
1125  
1126  
1127  
1128  
1129  
1130  
1131  
1132  
1133  
1134  
1135  
1136  
1137  
1138  
1139  
1140  
1141  
1142  
1143  
1144  
1145  
1146  
1147  
1148  
1149  
1150  
1151  
1152  
1153  
1154  
1155  
1156  
1157  
1158  
1159  
1160  
1161  
1162  
1163  
1164  
1165  
1166  
1167  
1168  
1169  
1170  
1171  
1172  
1173  
1174  
1175  
1176  
1177  
1178  
1179  
1180  
1181  
1182  
1183  
1184  
1185  
1186  
1187  
1188  
1189  
1190  
1191  
1192  
1193  
1194  
1195  
1196  
1197  
1198  
1199  
1200  
1201  
1202  
1203  
1204  
1205  
1206  
1207  
1208  
1209  
1210  
1211  
1212  
1213  
1214  
1215  
1216  
1217  
1218  
1219  
1220  
1221  
1222  
1223  
1224  
1225  
1226  
1227  
1228  
1229  
1230  
1231  
1232  
1233  
1234  
1235  
1236  
1237  
1238  
1239  
1240  
1241  
1242  
1243  
1244  
1245  
1246  
1247  
1248  
1249  
1250  
1251  
1252  
1253  
1254  
1255  
1256  
1257  
1258  
1259  
1260  
1261  
1262  
1263  
1264  
1265  
1266  
1267  
1268  
1269  
1270  
1271  
1272  
1273  
1274  
1275  
1276  
1277  
1278  
1279  
1280  
1281  
1282  
1283  
1284  
1285  
1286  
1287  
1288  
1289  
1290  
1291  
1292  
1293  
1294  
1295  
1296  
1297  
1298  
1299  
1300  
1301  
1302  
1303  
1304  
1305  
1306  
1307  
1308  
1309  
1310  
1311  
1312  
1313  
1314  
1315  
1316  
1317  
1318  
1319  
1320  
1321  
1322  
1323  
1324  
1325  
1326  
1327  
1328  
1329  
1330  
1331  
1332  
1333  
1334  
1335  
1336  
1337  
1338  
1339  
1340  
1341  
1342  
1343  
1344  
1345  
1346  
1347  
1348  
1349  
1350  
1351  
1352  
1353  
1354  
1355  
1356  
1357  
1358  
1359  
1360  
1361  
1362  
1363  
1364  
1365  
1366  
1367  
1368  
1369  
1370  
1371  
1372  
1373  
1374  
1375  
1376  
1377  
1378  
1379  
1380  
1381  
1382  
1383  
1384  
1385  
1386  
1387  
1388  
1389  
1390  
1391  
1392  
1393  
1394  
1395  
1396  
1397  
1398  
1399  
1400  
1401  
1402  
1403  
1404  
1405  
1406  
1407  
1408  
1409  
1410  
1411  
1412  
1413  
1414  
1415  
1416  
1417  
1418  
1419  
1420  
1421  
1422  
1423  
1424  
1425  
1426  
1427  
1428  
1429  
1430  
1431  
1432  
1433  
1434  
1435  
1436  
1437  
1438  
1439  
1440  
1441  
1442  
1443  
1444  
1445  
1446  
1447  
1448  
1449  
1450  
1451  
1452  
1453  
1454  
1455  
1456  
1457  
1458  
1459  
1460  
1461  
1462  
1463  
1464  
1465  
1466  
1467  
1468  
1469  
1470  
1471  
1472  
1473  
1474  
1475  
1476  
1477  
1478  
1479  
1480  
1481  
1482  
1483  
1484  
1485  
1486  
1487  
1488  
1489  
1490  
1491  
1492  
1493  
1494  
1495  
1496  
1497  
1498  
1499  
1500  
1501  
1502  
1503  
1504  
1505  
1506  
1507  
1508  
1509  
1510  
1511  
1512  
1513  
1514  
1515  
1516  
1517  
1518  
1519  
1520  
1521  
1522  
1523  
1524  
1525  
1526  
1527  
1528  
1529  
1530  
1531  
1532  
1533  
1534  
1535  
1536  
1537  
1538  
1539  
1540  
1541  
1542  
1543  
1544  
1545  
1546  
1547  
1548  
1549  
1550  
1551  
1552  
1553  
1554  
1555  
1556  
1557  
1558  
1559  
1560  
1561  
1562  
1563  
1564  
1565  
1566  
1567  
1568  
1569  
1570  
1571  
1572  
1573  
1574  
1575  
1576  
1577  
1578  
1579  
1580  
1581  
1582  
1583  
1584  
1585  
1586  
1587  
1588  
1589  
1590  
1591  
1592  
1593  
1594  
1595  
1596  
1597  
1598  
1599  
1600  
1601  
1602  
1603  
1604  
1605  
1606  
1607  
1608  
1609  
1610  
1611  
1612  
1613  
1614  
1615  
1616  
1617  
1618  
1619  
1620  
1621  
1622  
1623  
1624  
1625  
1626  
1627  
1628  
1629  
1630  
1631  
1632  
1633  
1634  
1635  
1636  
1637  
1638  
1639  
1640  
1641  
1642  
1643  
1644  
1645  
1646  
1647  
1648  
1649  
1650  
1651  
1652  
1653  
1654  
1655  
1656  
1657  
1658  
1659  
1660  
1661  
1662  
1663  
1664  
1665  
1666  
1667  
1668  
1669  
1670  
1671  
1672  
1673  
1674  
1675  
1676  
1677  
1678  
1679  
1680  
1681  
1682  
1683  
1684  
1685  
1686  
1687  
1688  
1689  
1690  
1691  
1692  
1693  
1694  
1695  
1696  
1697  
1698  
1699  
1700  
1701  
1702  
1703  
1704  
1705  
1706  
1707  
1708  
1709  
1710  
1711  
1712  
1713  
1714  
1715  
1716  
1717  
1718  
1719  
1720  
1721  
1722  
1723  
1724  
1725  
1726  
1727  
1728  
1729  
1730  
1731  
1732  
1733  
1734  
1735  
1736  
1737  
1738  
1739  
1740  
1741  
1742  
1743  
1744  
1745  
1746  
1747  
1748  
1749  
1750  
1751  
1752  
1753  
1754  
1755  
1756  
1757  
1758  
1759  
1760  
1761  
1762  
1763  
1764  
1765  
1766  
1767  
1768  
1769  
1770  
1771  
1772  
1773  
1774  
1775  
1776  
1777  
1778  
1779  
1780  
1781  
1782  
1783  
1784  
1785  
1786  
1787  
1788  
1789  
1790  
1791  
1792  
1793  
1794  
1795  
1796  
1797  
1798  
1799  
1800  
1801  
1802  
1803  
1804  
1805  
1806  
1807  
1808  
1809  
1810  
1811  
1812  
1813  
1814  
1815  
1816  
1817  
1818  
1819  
1820  
1821  
1822  
1823  
1824  
1825  
1826  
1827  
1828  
1829  
1830  
1831  
1832  
1833  
1834  
1835  
1836  
1837  
1838  
1839  
1840  
1841  
1842  
1843  
1844  
1845  
1846  
1847  
1848  
1849  
1850  
1851  
1852  
1853  
1854  
1855  
1856  
1857  
1858  
1859  
1860  
1861  
1862  
1863  
1864  
1865  
1866  
1867  
1868  
1869  
1870  
1871  
1872  
1873  
1874  
1875  
1876  
1877  
1878  
1879  
1880  
1881  
1882  
1883  
1884  
1885  
1886  
1887  
1888  
1889  
1890  
1891  
1892  
1893  
1894  
1895  
1896  
1897  
1898  
1899  
1900  
1901  
1902  
1903  
1904  
1905  
1906  
1907  
1908  
1909  
1910  
1911  
1912  
1913  
1914  
1915  
1916  
1917  
1918  
1919  
1920  
1921  
1922  
1923  
1924  
1925  
1926  
1927  
1928  
1929  
1930  
1931  
1932  
1933  
1934  
1935  
1936  
1937  
1938  
1939  
1940  
1941  
1942  
1943  
1944  
1945  
1946  
1947  
1948  
1949  
1950  
1951  
1952  
1953  
1954  
1955  
1956  
1957  
1958  
1959  
1960  
1961  
1962  
1963  
1964  
1965  
1966  
1967  
1968  
1969  
1970  
1971  
1972  
1973  
1974  
1975  
1976  
1977  
1978  
1979  
1980  
1981  
1982  
1983  
1984  
1985  
1986  
1987  
1988  
1989  
1990  
1991  
1992  
1993  
1994  
1995  
1996  
1997  
1998  
1999  
2000  
2001  
2002  
2003  
2004  
2005  
2006  
2007  
2008  
2009  
2010  
2011  
2012  
2013  
2014  
2015  
2016  
2017  
2018  
2019  
2020  
2021  
2022  
2023  
2024  
2025  
2026  
2027  
2028  
2029  
2030  
2031  
2032  
2033  
2034  
2035  
2036  
2037  
2038  
2039  
2040  
2041  
2042  
2043  
2044  
2045  
2046  
2047  
2048  
2049  
2050  
2051  
2052  
2053  
2054  
2055  
2056  
2057  
2058  
2059  
2060  
2061  
2062  
2063  
2064  
2065  
2066  
2067  
2068  
2069  
2070  
2071  
2072  
2073  
2074  
2075  
2076  
2077  
2078  
2079  
2080  
2081  
2082  
2083  
2084  
2085  
2086  
2087  
2088  
2089  
2090  
2091  
2092  
2093  
2094  
2095  
2096  
2097  
2098  
2099  
2100  
2101  
2102  
2103  
2104  
2105  
2106  
2107  
2108  
2109  
2110  
2111  
2112  
2113  
2114  
2115  
2116  
2117  
2118  
2119  
2120  
2121  
2122  
2123  
2124  
2125  
2126  
2127  
2128  
2129  
2130  
2131  
2132  
2133  
2134  
2135  
2136  
2137  
2138  
2139  
2140  
2141  
2142  
2143  
2144  
2145  
2146  
2147  
2148  
2149  
2150  
2151  
2152  
2153  
2154  
2155  
2156  
2157  
2158  
2159  
2160  
2161  
2162  
2163  
2164  
2165  
2166  
2167  
2168  
2169  
2170  
2171  
2172  
2173  
2174  
2175  
2176  
2177  
2178  
2179  
2180  
2181  
2182  
2183  
2184  
2185  
2186  
2187  
2188  
2189  
2190  
2191  
2192  
2193  
2194  
2195  
2196  
2197  
2198  
2199  
2200  
2201  
2202  
2203  
2204  
2205  
2206  
2207  
2208  
2209  
2210  
2211  
2212  
2213  
2214  
2215  
2216  
2217  
2218  
2219  
2220  
2221  
2222  
2223  
2224  
2225  
2226  
2227  
2



Table 1

	Underlying layer	Hc <sub>⊥</sub> (A/m)	Hc <sub>//</sub> (A/m)	Hc <sub>⊥</sub> /Hc <sub>//</sub>	Perpendicular squareness ratio
Example 1	Fe/Ru	222780	103490	2.15	0.97
Example 2	FeTaC/Ru	244110	106650	2.29	0.99
Example 3	FeZrN/Ru	240160	105860	2.27	0.98
Example 4	FeCo/Ru	249640	108230	2.31	1.00
Example 5	CoZrNb/Ru	209350	115340	1.82	0.97
Example 6	Co/Ru	263070	96380	2.73	1.00
Example 7	CoCr/Ru	271760	97960	2.77	0.99
Example 8	Ru/CoCr	269390	94800	2.84	0.98
Comparative Example 1	Cr	83740	229100	0.37	0.15
Comparative Example 2	Fe	27650	18960	1.32	0.02
Comparative Example 3	FeTaC	15010	15800	0.95	0.01
Comparative Example 4	FeZrN	14220	12640	1.13	0.01
Comparative Example 5	FeCo	16590	13430	1.24	0.02
Comparative Example 6	CoZrNb	13430	15800	0.85	0.01
Comparative Example 7	Co	33970	25280	1.34	0.05
Comparative Example 8	CoCr	180120	117710	1.53	0.99
Comparative Example 9	Ru	199080	131930	1.51	0.85

A perpendicular orientation is improved with increase in the ratio  $H_{c\perp}/H_{c//}$  shown in Table 1, and an read output is increased in the case where the perpendicular squareness ratio shown in Table 1 is as close to 1 as possible so as to provide an excellent perpendicular magnetic recording medium. In each of Comparative Example 1, the ratio  $H_{c\perp}/H_{c//}$  was smaller than 1, and the perpendicular squareness ratio was small, indicating that a areal orientation was formed in each of these Comparative Examples. Also, in each of Comparative Examples 2 to 7, the  $H_{c\perp}$ ,  $H_{c//}$  and perpendicular squareness ratio were more smaller the media have approximately complete areal orientation. This is because the soft magnetic layer is not partitioned magnetically with the recording layer so that the properties of the soft magnetic layer having high magnetic moment is predominant. However the properties of the recording layer was not influenced to the whole properties, therefore it is found that the perpendicular orientation of the recording layer is weak, and the areal orientation thereof is strong. Comparative Examples 8 and 9, which were not sufficient in terms of the perpendicular orientation, exhibited the most satisfactory characteristics among the Comparative Examples.

On the other hand, any of the  $H_{c\perp}/H_{c//}$  ratio and the perpendicular squareness ratio in any of Examples 1

to 9 of the present invention was found to be higher than that for any of Comparative Examples 8 and 9. In addition, the squareness ratio was substantially 1 in any of the Examples of the present invention.

5 These clearly support that the characteristics of the perpendicular magnetic recording medium are markedly improved in the present invention. The experimental data clearly support that, an under layer, which fails to exhibit a sufficient perpendicular  
10 orientation when used singly, produces the effect of improving the crystallinity of ruthenium when the under layer is used in combination with another under layer containing ruthenium as a main component. In this fashion, the present invention permits obtaining  
15 a Co-based magnetic layer exhibiting excellent perpendicular orienting properties, making it possible to obtain a perpendicular magnetic recording medium exhibiting satisfactory characteristics including a high coercive force and a high read output.

20 Example 9:

A magnetic recording medium was obtained as in Example 1, except that a Ti layer having a thickness of about 40 nm was formed as the first under layer in place of the Fe layer. The magnetic characteristics of  
25 the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Example 10:

A magnetic recording medium was obtained as in Example 1, except that a TiCr layer having a thickness of about 40 nm was formed as the first under layer in place of the Fe layer. The TiCr layer was formed by the sputtering of a target having a composition of Ti-Cr (10 at%) under an Ar gas atmosphere. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Example 11:

A magnetic recording medium was obtained as in Example 1, except that a TiN layer having a thickness of about 35 nm was formed as the first under layer in place of the Fe layer. The TiN layer was formed by the sputtering of a target having a composition of Ti-N 50 at% under an Ar gas atmosphere. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Example 12:

A magnetic recording medium was obtained as in Example 1, except that a Sendust layer having a thickness of about 30 nm was formed as the first under layer in place of the Fe layer. The Sendust layer was formed by the sputtering of a target having a composition of Fe 85 at%-Al 5 at%-Si 10 at% under an

Ar gas atmosphere. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Comparative Example 10:

5           A magnetic recording medium was obtained as in Example 9, except that a second under layer was not formed. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

10          Comparative Example 11:

          A magnetic recording medium was obtained as in Example 10, except that a second under layer was not formed. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

15          Comparative Example 12:

          A magnetic recording medium was obtained as in Example 11, except that a second under layer was not formed. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Comparative Example 13:

25           A magnetic recording medium was obtained as in Example 1, except that a vanadium layer having a thickness of 41 nm was formed as the first under layer in place the Fe layer, and that a second under layer was not formed. The magnetic characteristics of the

magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Comparative Example 14:

5 A magnetic recording medium was obtained as in Example 12, except that a second under layer was not formed. The magnetic characteristics of the magnetic recording medium thus obtained were measured as in Example 1. Table 2 shows the results.

Table 2

	Under layer	Hc $\perp$ (A/m)	Hc// (A/m)	Hc $\perp$ /Hc//	Perpendicular squareness ratio
Example 9	Ti/Ru	270970	93220	2.91	0.99
Example 10	TiCr/Ru	282030	99540	2.83	1.0
Example 11	TiN/Ru	273340	96380	2.84	0.98
Example 12	Sendust/Ru	203820	112970	1.80	0.96
Comparative Example 10	Ti	200660	166690	1.20	0.73
Comparative Example 11	TiCr	186440	165110	1.13	0.62
Comparative Example 12	TiN	86110	145360	0.59	0.18
Comparative Example 13	V	90850	226730	0.40	0.14
Comparative Example 14	Sendust	18170	15010	1.21	0.01

Where the magnetic recording medium including a soft magnetic layer in addition to the recording magnetic layer is measured by VSM, the resultant characteristics includes both of two characteristics relating to the soft magnetic layer and the magnetic recording layer. However since it is possible to interpret the characteristics separately in respect of Example 12, the values for the recording layer approximately alone are shown.

As apparent from Table 2, the value of  $H_{c\perp}/H_{c//}$  for each of Comparative Examples 12 and 13 was not larger than 1, and the perpendicular squareness ratio was also small, supporting that a areal orientation was formed in each of these Comparative Examples. Also, in Comparative Example 14, the  $H_{c\perp}$ ,  $H_{c//}$  and perpendicular squareness ratio were more smaller the media have approximately complete areal orientation. This is because the soft magnetic layer is not partitioned magnetically with the recording layer so that the properties of the soft magnetic layer having high magnetic moment is predominant. However the properties of the recording layer was not influenced to the whole properties, therefore it is found that the perpendicular orientation of the recording layer is weak, and the areal orientation thereof is strong. A areal orientation was not recognized in each of Comparative Examples 10 and 11. However, the value of



Hc// was large, i.e., not smaller than 2 kOe, and the perpendicular squareness ratio was 0.6 to 0.7 in each of these Comparative Examples, supporting that the perpendicular orientation was insufficient.

5           As described above, both of Examples 8 and 9 of the present invention exhibited the values of  $H_{c\perp}/H_{c//}$  and the perpendicular squareness ratio larger than those for Comparative Example 15, and the squareness ratio was substantially 1 in each of Examples 9-12 of  
10           the present invention. These clearly support that the characteristics as the perpendicular magnetic recording medium were markedly improved in the present invention. This indicates that, where an under layer is formed under a Ru layer, it is possible to improve the  
15           crystallinity of Ru, though when such an under layer is singly formed under the magnetic recording layer, the perpendicular orientation of the magnetic recording layer is insufficient. Such being the situation, it has been clarified that it is possible to obtain a  
20           CoPtO-based magnetic layer exhibiting an excellent perpendicular orientation in the case where an under layer of a laminate structure is used as an under layer of the CoPtO-series magnetic layer, said laminate structure consisting of a first under layer made of Ti, TiCr, TiN, V or Sendust and formed on the substrate and  
25           a second under layer formed on the first under layer and made of Ru. As a result, it is possible to obtain

a perpendicular magnetic recording medium having a high coercive force and exhibiting a high reproducing output.

5 In each of the Examples described above, a glass substrate was used as the nonmagnetic substrate. However, the similar effect can be obtained in the case where an Al-based alloy substrate, a Si single crystal substrate having an oxidized surface, or a substrate having, for example, NiP plated on the surface is used  
10 as the nonmagnetic substrate. Also, the film formation was performed by a sputtering method in each of the Examples described above. However, it is also possible to employ other film formation methods such as a vacuum vapor deposition method, with substantially the same  
15 effect.

Example 13:

A magnetic recording medium was obtained as in Example 1, except that a FeAlSi soft magnetic layer was formed on a substrate by sputtering a target having a  
20 composition of Fe-5 at%-Al 10 at%-Si under an Ar gas atmosphere, and that a V layer having a thickness of 41 nm was formed as the first under layer in place of the Fe layer. The magnetic characteristics of the magnetic recording medium thus obtained were measured  
25 as in Example 1. The other magnetic recording media were obtained and the magnetic characteristics of them were measured as the same way except that the

compositions were Fe 10 at%-Ta 10 at%-C, Fe 10 at%-Zr  
10 at%-N, Fe 50 at%-Co, and Co 5 at% Zr 10 at%-Nb,  
respectively. It has been found that the magnetic  
recording media thus obtained were satisfactory in each  
5 of the ratio of the perpendicular coercive force to the  
areal coercive force and the perpendicular squareness  
ratio.

Example 14:

A magnetic recording medium was obtained as in  
10 Example 1, except that a Cr layer having a thickness of  
about 40 nm was formed as the first under layer in  
place of the Fe layer. The magnetic characteristics of  
the magnetic recording medium thus obtained were  
measured as in Example 1. It has been found that  
15 the magnetic recording medium thus obtained was  
satisfactory in each of the ratio of the perpendicular  
coercive force to the areal coercive force and the  
perpendicular squareness ratio.

Additional experiments were conducted in line with  
20 Examples 1 to 14, except that alloy layers of RuCr and  
RuCo were used in place of the Ru under layer, with  
substantially the same improving effects.

Further, additional experiments were conducted by  
using each of alloy layers of CoPt, CoCr and CoCrPt as  
25 the magnetic recording layer in place of the CoPtO  
recording layer, with substantially the same improving  
effects.

Still further, additional experiments were conducted by using as a magnetic recording layer a multi-layered film of Co/Pd, Co/Pt or Co/Ru in place of the CoPtO recording layer, said multi-layered film being prepared by alternately laminating 20 times a Co layer having a thickness of about 0.3 nm and a Pd layer, a Pt layer or a Ru layer each having a thickness of about 1 nm, with substantially the same improving effects.

Example 15:

Perpendicular magnetic recording media were prepared as in Examples 1 to 14, except that perpendicular magnetic recording layers of a laminate structure were formed in place of each one CoPtO magnetic layer formed in Examples 1 to 14, said laminate structure being prepared by forming a first layer of a CoPtCrO magnetic layer having a thickness of 13 nm, followed by forming a Ru layer having a thickness of 4 nm as a nonmagnetic intermediate layer of the recording layer and subsequently forming again a second layer of a CoPtCrO magnetic layer.

The magnetic characteristics of each of the magnetic recording media thus obtained were measured, with the result that the recording layer of the laminate structure was found to be superior to the recording layer of a single layer structure in each of  $H_{c\perp}$  and  $H_{c\perp}/H_{c//}$ . The experimental data clearly support that

the perpendicular orientation and the perpendicular coercive force of the perpendicular magnetic recording medium can be improved by employing a perpendicular magnetic recording layer of a laminate structure and by  
5 using a Ru layer as a nonmagnetic intermediate layer of the laminate structure.

Example 16:

Perpendicular magnetic recording media were prepared as in Examples 1 to 12 and 15, except that  
10 a so-called "perpendicular double layered medium" was formed by forming a FeAlSi soft magnetic layer between the nonmagnetic substrate and the first under layer. The magnetic characteristics of each of the resultant perpendicular double layer media were evaluated, and  
15 the characteristics of the recording layer alone were evaluated by separating the FeAlSi soft magnetic layer, so as to obtain the results substantially equal to those of Examples 1 to 12 and 15. In other words, the characteristics as the perpendicular magnetic recording  
20 medium were found to have been improved, compared with Comparative Examples 1 to 14. Such being the situation, it has been clarified that the effect of the FeAlSi soft magnetic layer of the laminate structure can be maintained even where the FeAlSi layer is  
25 formed to form a perpendicular double layer medium, making it possible to improve the perpendicular orientation, the perpendicular coercive force and the

reproducing output of the perpendicular magnetic recording medium.

Example 17:

Perpendicular magnetic recording media were  
5 prepared as in Examples 1 to 12 and 15, except that a  
so-called "perpendicular double layered medium" was  
formed by forming a FeTaC soft magnetic layer between  
the nonmagnetic substrate and the first under layer.  
The magnetic characteristics of each of the resultant  
10 perpendicular double layer media were evaluated, and  
the characteristics of the recording layer alone were  
evaluated by separating the FeTaC soft magnetic layer,  
so as to obtain the results substantially equal to  
those of Examples 1 to 12 and 15. In other words, the  
15 characteristics as the perpendicular magnetic recording  
medium were found to have been improved, compared  
with Comparative Examples 1 to 14. Such being the  
situation, it has been clarified that the effect of  
the under layer of the laminate structure can be  
20 maintained even where the FeTaC layer is formed to  
form a perpendicular double layer medium, making it  
possible to improve the perpendicular orientation,  
the perpendicular coercive force and the reproducing  
output of the perpendicular magnetic recording medium.

25 Example 18:

Perpendicular magnetic recording media were  
prepared as in Examples 1 to 12 and 15, except that

a so-called "perpendicular double layered medium" was formed by forming a FeZrN soft magnetic layer between the nonmagnetic substrate and the first under layer. The magnetic characteristics of each of the resultant perpendicular double layer media were evaluated, and the characteristics of the recording layer alone were evaluated by separating the FeZrN soft magnetic layer, so as to obtain the results substantially equal to those of Examples 1 to 12 and 15. In other words, the characteristics as the perpendicular magnetic recording medium were found to have been improved, compared with Comparative Examples 1 to 14. Such being the situation, it has been clarified that the effect of the under layer of the laminate structure can be maintained even where the FeZrN layer is formed to form a perpendicular double layer medium, making it possible to improve the perpendicular orientation, the perpendicular coercive force and the reproducing output of the perpendicular magnetic recording medium.

Example 19:

Perpendicular magnetic recording media were prepared as in Examples 1 to 12 and 15, except that a so-called "perpendicular double layered medium" was formed by forming a FeCo soft magnetic layer between the nonmagnetic substrate and the first under layer. The magnetic characteristics of each of the resultant perpendicular double layer media were evaluated, and

the characteristics of the recording layer alone were evaluated by separating the FeCo soft magnetic layer, so as to obtain the results substantially equal to those of Examples 1 to 12 and 15. In other words, the characteristics as the perpendicular magnetic recording medium were found to have been improved, compared with Comparative Examples 1 to 14. Such being the situation, it has been clarified that the effect of the under layer of the laminate structure can be maintained even where the FeCo layer is formed to form a perpendicular double layer medium, making it possible to improve the perpendicular orientation, the perpendicular coercive force and the reproducing output of the perpendicular magnetic recording medium.

Example 20:

Perpendicular magnetic recording media were prepared as in Examples 1 to 15, except that a so-called "perpendicular double layer medium" was formed by forming a CoZrNb soft magnetic layer between the nonmagnetic substrate and the first under layer. The magnetic characteristics of each of the resultant perpendicular double layer media were evaluated, and the characteristics of the recording layer alone were evaluated by separating the CoZrNb soft magnetic layer, so as to obtain the results substantially equal to those of Examples 1 to 12 and 15. In other words, the characteristics as the perpendicular magnetic recording



medium were found to have been improved, compared with Comparative Examples 1 to 14. Such being the situation, it has been clarified that the effect of the under layer of the laminate structure can be maintained even where the CoZrNb layer is formed to form a perpendicular double layer medium, making it possible to improve the perpendicular orientation, the perpendicular coercive force and the reproducing output of the perpendicular magnetic recording medium.

It should be noted that the materials of the soft magnetic layer are not limited to those used in the Examples of the present invention described above. Particularly, it was found possible to obtain the similar effect by using the other soft magnetic materials in the case of forming an amorphous layer such as a carbon layer on the soft magnetic layer.

FIG. 4 shows an example of the magnetic recording apparatus in which the perpendicular magnetic recording media according to the first to sixth aspects of the present invention can be applied. As shown in the drawing, a magnetic disc 121 of a hard structure for recording information is mounted to a spindle 122 and is rotated at a predetermined speed by a spindle motor (not shown). A slider 123 has a magnetic head is provided on the tip of a suspension 124 formed in a thin plate-like leaf spring which access to the magnetic disc 121 to read and write signals.

The suspension 124 is connected to one end portion of an arm 125 having a bobbin etc. for holding a driving coil (not shown).

5 A voice coil motor 126, which is a kind of a linear motor, is mounted on the other end portion of the arm 125. The voice coil motor 126 comprises a driving coil (not shown) wound up to the bobbin portion of the arm 125 and a magnetic circuit consisting of a permanent magnet arranged to have the driving coil held  
10 therein and a yoke positioned to face the permanent magnet.

The arm 125 is held by ball bearings mounted in the upper and lower portions of a stationary shaft 127 so as to be rotated and swung by the voice coil motor  
15 126. In other words, the position of the slider 123 on the magnetic disc 121 is controlled by the voice coil motor 126. Incidentally, a reference numeral 128 in FIG. 4 denotes a lid.

The perpendicular magnetic recording media  
20 according to the first to sixth aspects of the present invention have good perpendicular orientation and perpendicular coercive force in the recording layer thereof. Therefore a hard disk device exhibiting high density and high read output can be realized by using  
25 one of such media.

Additional advantages and modifications will readily occur to those skilled in the art. Therefore,

the invention in its broader aspects is not limited to the specific details and representative embodiments shown and described herein. Accordingly, various modifications may be made without departing from the spirit or scope of the general inventive concept as defined by the appended claims and their equivalents.

5